

Elastollan® S-85AN

Thermoplastic Polyurethane Elastomer (Polyester)

BASF Corp. Thermoplastic Polyurethanes

Product Description

Elastollan® S series of products are polyester-based thermoplastic polyurethanes that exhibit good hydrolytic stability. They also exhibit good oil, fuel and solvent resistance. These products can be injection molded, blow molded and extruded. All grades should be dried before processing. Elastollan® products can be stored for up to 1 year in their original container. Containers should be stored in a cool, dry area.

Products with an N designation do not contain hydrolytic stabilizers.

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Fuel Resistant	• Oil Resistant	• Solvent Resistant
	• Good Chemical Resistance		
Forms	• Granules		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792

Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance			ASTM D1044
1000 Cycles, 1000 g, H-18 Wheel	25.0	mg	

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.90	MPa	
300% Strain	14.0	MPa	
Tensile Strength (Yield)	34.0	MPa	ASTM D412
Tensile Elongation (Break)	690	%	ASTM D412
Elongation Set After Break	35	%	ASTM D412
Tear Strength ²	104	kN/m	ASTM D624

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	83 to 87		ASTM D2240

Injection	Nominal Value	Unit
Drying Temperature	79.4 to 90.6	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Suggested Max Regrind	30	%
Rear Temperature	182	°C
Middle Temperature	188	°C
Front Temperature	193	°C
Nozzle Temperature	196	°C
Processing (Melt) Temp	188 to 199	°C
Mold Temperature	21.1 to 37.8	°C
Injection Pressure	3.45 to 10.3	MPa
Back Pressure	0.517 to 1.03	MPa
Screw Speed	30 to 120	rpm
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	
Screw Compression Ratio	2.0:1.0 to 3.0:1.0	

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！